



## HD010WB

High Density Polyethylene Black Compound Resin

Special Characteristics: PlastMate HD010WB is black bimodal high density polyethylene compound with excellent ESCR, and contains well-dispersed of high-quality carbon black for excellent weathering and UV resistance. This grade is suitable for producing medium to high voltage power cable jacketing.

Typical Applications: Medium to High power cable jacketing

International Standard: ASTM D1248 (Type III, Class C, Category 5)\*, IEC60502-02 (ST7)\*\*, IEC60840 (ST7)\*\*

\*PlastMate HD010WB grade meets the following raw materials specifications.

\*\*Cable jacketing covered with PlastMate HD010WB is processed using sound commercial extrusion practices as well as the appropriate testing procedures, should meet the following cable specification.

## Typical Properties:

Properties	PlastMate HD010WB	Unit	Test Method
Physical and Mechanical Properties			
Melt Index (190°C, 2.16 Kg)	0.13	g/10 min	ISO 1133
Density	0.958	g/cm <sup>3</sup>	ISO 1183
Carbon Black Content	2.5	%	ISO 6964
Tensile Strength	33	MPa	ISO 527
Elongation at Break	900	%	ISO 527
Oxidation Induction Time (210°C)	60	Min	ISO 11357
ESCR, F <sub>0</sub> (Condition B, 10% Igepal, 50°C)	> 5,000	Hours	ASTM D1693
Flexural Modulus	800	MPa	ISO 178
Durometer Hardness	64	Shore D	ISO 868
Electrical Properties			
Volume Resistivity	10 <sup>17</sup>	Ohm.cm	ASTM D257
Dielectric Strength	17	kV/mm	ASTM D149
Dielectric Constant, 1 MHz	2.5	-	ASTM D150
Dissipation Factor, 1 MHz	0.015		ASTM D150

## Recommendation:

Recommended melt temperature: 180 - 230°C

Disclaimer: To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication; however, we do not assume any liability what so ever for the accuracy and completeness of such information. We make no warranties which extend beyond the description contained herein. Nothing herein shall constitute any implied warranty of merchantability or fitness for a particular purpose. It is the customer's responsibility to inspect and test our products in order to satisfy itself as to the suitability of the products for the customer's particular purpose. The customer is responsible for the appropriate, safe and legal use, processing and handling of our products. No liability can be accepted in respect of the use of our products in conjunction with other materials. The information contained herein relates exclusively to our products when not used in conjunction with any third party materials.

Note: Properties reported here are typical values of the product, not to be considered as specifications. GC makes no representations as to the accuracy or completeness of the information contained herein.