



HD7808B

High Density Polyethylene Resin

Special Characteristics: InnoPlus HD7808B is high molecular weight high density polyethylene blow molding grade which is recommended for Intermediate bulk containers and large size drum. It has excellent processability and exhibits very high impact strength, stiffness and superior environmental stress cracking resistance. Furthermore, it is UV stabilizer added that give the excellent UV resistance for our outdoor application.

Typical Applications : Hazardous chemical, Agricultural chemical intermediate bulk containers and drums.

Typical Properties :

Properties	HD7808B	Unit	Test Method
Properties			
Physical Properties			
/lelt Flow Rate (5 kg/190 °C)	0.2	g/10 min	ASTM D1238
/lelt Flow Rate (21.6 kg/190 °C)	6.0	g/10 min	ASTM D1238
Density	0.950	g/cm ³	ASTM D1505
/icat Softening Point @ 10 N, 50°C/hr	125	°C	ASTM D1525
Aelting Point	130	°C	ASTM D3418
Aechanical Properties			
ensile Strength @ Yield	300	kg/cm ²	ASTM D638
ensile Strength @ Break	370	kg/cm ²	ASTM D638
longation @ Break	850	%	ASTM D638
lexural Modulus	12000	kg/cm ²	ASTM D790
lotched Izod Impact Strength	72 (NB)*	kg.cm/cm	ASTM D256
Durometer hardness	61	Shore D	ASTM D2240
ESCR, F ₅₀ (Condition B, 25 % Igepal)	>1000	hrs	ASTM D1693

* NB = Non Break

Note : Properties reported here are typical values of the product, not to be considered as specifications. PTT Global Chemical makes no representations as to the accuracy or completeness of the information contained herein.

GC Marketing Solutions Company Limited Energy Complex Building A, 9th Floor, 555/1 Vibhavadi Rangsit Road, Chatuchak, Bangkok 10900 Tel: 66 2140 4488 Fax: 66 2140 4333

Revised Date : Oct, 2021 Page 1/2





HD7808B

High Density Polyethylene Resin

Processing Condition :

Extruder temperature :	175 - 190 °C
Die temperature :	180 - 200 °C

FDA Statement :

HDPE under the brand InnoPlus complies with U.S. FDA 21 CFR 177.1520 (c) (2.1) and (2.2) regulation for polyethylene used in articles that contact food suitable for articles used for packaging or holding food during cooking.

Disclaimer :

This Applications specified herein is for reference only and not suitable for using in the manufacturing of any products in medical and pharmaceutical sectors.

- Determination of suitability of the product for the use and purpose shall be the customer's responsibility. Customer is obligated to inspect and test the product for such suitability. Customer is responsible for appropriate, safe, legal use processing and handling of the product.
- To our best knowledge, information contained herein is true and accurate as of the date of its publication. However, we make no representations or warranties with respect to accuracy, reliability and completeness of the information contained herein for any purpose.
- No warranties, express or implied, which extend beyond the description herein are given by us. Nothing herein shall constitute any implied warranty of merchantability or fitness for a particular purpose.

 Note : Properties reported here are typical values of the product, not to be considered as specifications.

 PTT Global Chemical makes no representations as to the accuracy or completeness of the information contained herein.