



Revised Date: October 2025

LD2426F

Low Density Polyethylene Resin

Special Characteristics: InnoPlus LD2426F is produced by high pressure tubular process, a technology licensed by LyondellBasell. This grade offers excellent processability for increased extruder outputs, good balance of mechanical and optical properties, exceptional clarity and gloss. Typical Applications: InnoPlus LD2426F is recommended for producing the heavy duty films, agricultural films, shrink films, tubes and small extrusion blow molding containers.

Additives: Slip 500 ppm and Antiblock 700 ppm.

Typical Properties:

Properties		LD2426F	Unit	Test Method		
Physical Properties (Based on pellets and press-molded sheet)						
Melt Flow Rate (190 °C, 2.16 kg)	0.75	g/10 min	ISO 1133		
Density		0.922	g/cm ³	ISO 1183		
Melting Temperature		112	°C	ISO 11357		
Vicat softening point		95	°C	ASTM D1525		
Film Properties* (Based on blown film)						
				100 507		

23 / 18	MPa	ISO 527
350 / 630	%	ISO 527
120	g	ASTM D1709
6	%	ASTM D1003
60	-	ASTM D2457
	350 / 630 120 6	350 / 630 % 120 g 6 %

^{*} film properties obtained from 50 microns film which was blown film extruded at blow up ratio 2.0

Recommendation:

The recommended temperature setting is in the range of 170 - 220 $^{\circ}$ C

FDA Statement:

Food and Drug Administration US FDA 21 CFR 177.1520 and Commission Regulation (EU) 10/2011. More compliance regulations and standards that related to the product shall be exhibited in Product Regulatory Certificate (PRC) document.

Disclaimer: To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication; however, we do not assume any liability what so ever for the accuracy and completeness of such information. We make no warranties which extend beyond the description contained herein. Nothing herein shall constitute any implied warranty of merchantability or fitness for a particular purpose. It is the customer's responsibility to inspect and test our products in order to satisfy itself as to the suitability of the products for the customer's particular purpose. The customer is responsible for the appropriate, safe and legal use, processing and handling of our products. No liability can be accepted in respect of the use of our products in conjunction with other materials. The information contained herein relates exclusively to our products when not used in conjunction with any third party materials.

Note: Properties reported here are typical values of the product, not to be considered as specifications.

GC makes no representations as to the accuracy or completeness of the information contained herein.